



ReflectASeal

Epoxy Coatings & Waterproofing Systems

REFLECTASEAL-1070 Silicone (70% Silicone Roof Coating) For Professional Use Only

PRODUCT INFORMATION

Product Type: A ready-to use, high solids, single component, solvent borne, moisture cure fluid applied silicone coating.

General Properties: Breathable membrane possessing superior weathering and water resistance characteristics.

Recommended Uses: Provides elemental protection for architectural surfaces such as vertical walls, masonry, concrete, metal, single ply roof membranes and sprayed-in-place urethane foam systems.

Product Limitations: Not recommended for continuous immersion service, for use in cryogenic tank, or cold storage roofing applications without a vapor barrier, or directly over Modified Bitumen, Asphalt or Coal Tar Built-Up roofing systems without a sealer. Note: ReflectASeal, LLC recommends any subsequent coats of silicone be completed within 48 hours to ensure good adhesion of the silicone to the previous coat.

Ponding Water:

- **ReflectASeal-1070 Warranties do not cover damage due to ponding water.**
- The National Roofing Contractors Association considers ponding water on any roof unacceptable. (See the NRCA Roofing and Waterproofing Manual).

Please consult ReflectASeal Technical Department for any specific questions regarding the application of this product.

Flammability Characteristics: ReflectASeal-1070 Coatings carry Class "A" Non-Combustible and Class "B" Combustible credentials as tested under UL 790 procedures over spray foam and single ply roofing systems. Contact ReflectASeal or refer to the UL directory for specific information.

Approvals: ReflectASeal-1070 Series has additional approvals with FM, CRRC, Energy Star, Miami-Dade, and is California Title 24 compliant.

Standard Colors: White, Light Grey, and Dark Grey.
Special colors upon request at additional charge.
Allow additional 15 days for non-standard colors.

Physical Properties:

Material tested complies with all of the requirements of ASTM D 6694-01 Standard specification Liquid-Applied Silicone Coating

Tensile Strength:	486 psi at 73°F. \pm 20 700 psi at 0°F. \pm 20	(ASTM D-412)
Elongation: Initial	267% at 73°F. \pm 20 282% at 0°F. \pm 20	(ASTM D-412)

Reflectivity (White)	84%	C-1549
Emissivity (White)	.85	C-1371
SRI Value	105	
Permeability:	5.9	(ASTM E-96, Procedure B)
Tensile, set at 100% Elongation:	Nil.	
Temperature Stability Range:	-80 °F. to 350°F. (-37°C. to 177°C)	
Water Absorption:	0.1 weight % after 2 weeks at 75 °F. (24 °C)	(ASTM D-471)
Weathering/UV Resistance:	No degradation after 8,760 hours	(ASTM G-53)
Specific Gravity:	1.23 at 77°F. (25°C)	
Tack Free Time:	1 hour	
VOC:	<250 Grams/Liter	(ASTM-D-3960) EPA Method 24
Durometer Hardness:	50± 5 points	(Shore A)
Solids Content By Weight:	80% ± 2	(ASTM D-1644)
Solids Content By Volume:	69% ± 2	(ASTM D-2697)
Maximum Continuous Service Temperature:	185°F (85°C)	
Flash Point:	>105°F.	(ASTM D-93)
Cure Time:	2-8 Hours, depending upon temperature.	
Drying Time:	1 hour at 77°F.	
Shelf Life:	(UNOPENED CONTAINERS): 6 months when stored between 35°F. and 75° F.	

Ordering Information:

This product is available in 5-gallon pails (19 liters), and in 55-gallon drums containing 50 gallons (190 liters).

Shipping Information:

<u>Container Size</u>	<u>Class</u>
5 Gal.	55
50 Gal.	55

D.O.T. Classification: Roof Coating, Not Regulated

HMIS® Rating:

Health 2, Flammability 2, Reactivity 0, Protection X
0= Minimal 1=Slight 2=Moderate 3=Serious 4=Severe

APPLICATION PROCEDURES ReflectASeal-1070

Do Not Thin

SURFACE PREPARATION: All surfaces to be coated must be clean, dry, and paintable. It may be necessary to power wash and/or prime to enhance adhesion. See application specification for more details.

MIXING PROCEDURES: No thinning or reducing is necessary. Product may separate after shipping and storage, though it may still look mixed. When mixing becomes necessary we recommend the use of a 3/4 horsepower or larger air operated mixer with a blade capable of uniformly mixing the entire container. When product is in 5-gallon pails use a 3" minimum diameter-mixing blade, or hand mixing with a suitable blade is acceptable. When product is in drums, use a 6" minimum diameter-mixing blade.

Containers are packaged with a layer of dry nitrogen gas, to keep latent moisture from prematurely starting the curing process. After opening a container, try to use it up as soon as possible, or reseal with a layer of argon or nitrogen gas.

Caution: Due To The Combustible Nature Of This Product, Do Not Use An Electric Mixer.

WEATHER RESTRICTIONS: It is not recommended that this product be applied at temperatures below 50° F. (10°C.), or if rain is expected within 1 hour of application. ReflectASeal-1070 may be applied at lower temperatures; however the cure time will be extended.

APPLICATION EQUIPMENT: This product may be sprayed, brushed, or rolled. Due to the high viscosity of the material, a high-pressure airless paint pump capable of producing a minimum of 3500 PSI at the spray gun head should be used. The pump should have a minimum of 3 gallons per minute output and be fed by a 5:1 transfer pump to prevent cavitation. Always use components rated for pump pressure. Hoses should be BUNA-N jacketed for prevention of moisture contamination. Hoses should have a minimum I.D. of 3/4" and an adequate working pressure. The spray gun should be high pressure (5000 PSI) with reverse-a-clean spray tip, having a minimum orifice of .030 and a 50° fan tip.

SYSTEM OPTIONS: This product can be used as a topcoat over ReflectASeal-101 base coats where improved traffic and impact resistant characteristics are required.

APPLICATION PROCEDURES: This product may be applied directly to any clean, dry surface. Polyurethane foam should be coated within 24 hours of application.

Subsequent coats should be applied within 48 hours of prior applications to insure full and uniform adhesion. Coating must be applied in 2 or 3 separate applications of contrasting colors, each applied at right angles to the previous coat. Coating must be evenly applied and pinhole-free.

Before applying a subsequent coat of this product the previous coat must be completely dry and cured. If any contamination of a thoroughly cured surface occurs, it must be washed with a chemical cleaner before applying subsequent coats. Coating must be extended beyond the substrate to create a self-terminating flashing. Consult ReflectASeal for recommended dry film thickness.

Due to the bond agent present in all coating, colors may be used as either a base or a topcoat. The coating will cure in 2-6 hours, dependent on weather conditions (such as temperature and humidity), after which another coat can be applied. A #11 ceramic roofing granule may be installed in the topcoat to improve aesthetics, traffic resistance and impact resistance.

RECOATING PROCEDURES: This product may be used to re-coat existing spray-in-place roofing systems. The surface to receive recoat must be thoroughly cleaned using power scrubber, pressure washer, chemical cleaners, or air wand. Surface must be completely dry before applying re-coat.

SAFETY PRECAUTIONS: This product contains combustible solvents. Keep coating material and cleaning solvents away from all sources of heat, sparks, flame, lighted smoking materials, or any other ignition source. Pumping equipment should be grounded to avoid accidental ignition due to static sparks.

Avoid breathing solvent vapors. Use an appropriate MESA/NIOSH approved respirator when exposure can exceed recommended PEL. This product is not recommended for interior use. Additional care must be taken to prevent roof top HVAC equipment from introducing evaporating solvent into interior areas during application. Building occupants should be warned of spray operations in process.

Installers should exercise caution during spray processes to avoid falls caused by stepping into slippery wet coating. Installers should read and understand all technical and informational literature on this product, including the MSDS, prior to use of the product.

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact ReflectASeal, LLC to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by ReflectASeal, LLC. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ReflectASeal, LLC EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.